

| Type Of Adhesive | Color | Packaging | Base | Viscosity (Brookfield) @ 200 C (392 F) in cPs (mPa.s) | Softening Point | Temperature Application Roller | Temperature Melting Pot | Edgebander Feed Speed Feet/Minute | Application |
|------------------|---------|------------|--------------------|---|-----------------|--------------------------------|-------------------------|-----------------------------------|---|
| HPK20 | Clear | 26 lb. Box | EVA Cartridge (45) | 75,000 cps | 110° C | 200°-220° C | 190°-200° C | 30 ft/min | PVC, ABS, Veneer, Polyester, Melamine, Solid Wood and HPL |
| HPK21 | Natural | 33 lb. Box | EVA Cartridge (45) | 90,000 cps | 108° C | 200°-220° C | 190°-200° C | 40 ft/min | PVC, ABS, Veneer, Polyester, Melamine, Solid Wood and HPL |
| KS208/2 | Natural | 55 lb. Bag | EVA Pellets | 130,000 cps | 110° C | 190°-210° C | 180°-200° C | 50 ft/min | PVC, ABS, Veneer, Polyester and Melamine |
| KS217 | Natural | 55 lb. Bag | EVA Pellets | 55,000 cps | 105° C | 190°-210° C | 180°-200° C | 40 ft/min | PVC, ABS, Veneer, Polyester, Melamine, Solid Wood and HPL |
| KS224/2 | Natural | 55 lb. Bag | EVA Pellets | 10,000 cps | 85° C | 120°-140° C | 120°-140° C | 30 ft/min | PVC, ABS, Veneer, Polyester and Melamine |
| KS351 | Clear | 55 lb. Bag | EVA Pellets | 75,000 cps | 110° C | 190°-200° C | 180°-200° C | 50 ft/min | PVC, ABS, Veneer, Polyester, Melamine, Solid Wood and HPL |